

# Technical Data Sheet

## Skydrol® PE-5

### Applications

- Aviation hydraulic fluid

### Product Description

Skydrol PE-5 was developed to meet and exceed the more demanding Type V fluid requirements. It features the longest fluid life of any commercially available fluid, low density and low viscosity at low temperature—an unbeatable combination of the best features for optimum fluid performance. Thermal stability is according to Airbus test method, Fluid life test with 0.5% moisture level.

### Typical Properties

Property	Test Method	Typical Value, Units
<b>General</b>		
Acid Number (mg KOH/g)		0.10 Maximum
Appearance		Clear, oily liquid
Autoignition Temperature	ASTM D 2155	400 °C (752 °F ) Minimum
Color		Purple, essentially equivalent to intensity and hue standard
Elemental Content		
Calcium		10 ppm, Maximum
Chlorine		50 ppm, Maximum
Potassium		26-41 ppm
Sodium		10 ppm, Maximum
Sulfur		1185-1540 ppm
Fire Point		
COC		177 °C (350 °F ) Minimum
Flash Point		
COC		160 °C (320 °F ) Minimum
Moisture		0.20 % Maximum
Particle Contamination <sup>a</sup>		
15-25 micron size		5,700 Maximum
25-50 micron size		1,012 Maximum
50-100 micron size		180 Maximum
5-15 micron size		32,000 Maximum
Over 100 micron size		32 Maximum
Pour Point		-62 °C (-80 °F ) Maximum
Specific Gravity		
@ 25°C/25°C		0.990-1.000
Viscosity		
@ 38°C (100°F)		9.02-10.02 cSt
@ -54°C (-65°F)		2000 cSt Maximum
@ 99°C (210°F)		3.11-3.51 cSt

<sup>a</sup>NAS 1638 particle counts per AS4059F

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

2/28/2018 11:35:39 AM

© 2020 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.