

LOCTITE[®] SF 7400[™]

Known as LOCTITE[®] 7400[™]
June 2014

PRODUCT DESCRIPTION

LOCTITE[®] SF 7400[™] provides the following product characteristics:

Technology	Solvent based
Chemical Type	Pigmented organic polymer
Appearance	Red liquid
Cure	Solvent evaporation
Application	Visible marker for use on electronics equipment

LOCTITE[®] SF 7400[™] is a solvent based dark red marking ink for use on electronic equipment. The product dries quickly and has excellent adhesion to a range of materials. It is ideal for tamper-proofing adjustment points or marking components to indicate they have been set or tested.

TYPICAL PROPERTIES

Viscosity, Brookfield, 20 °C, mPa·s (cP):	
Spindle 4, speed 60 rpm,	1,030
Solids Content, %	22.5
Tack Free Time (100 µm), minutes	5
Dry time (100 µm), hours	5 to 7
Flash Point - See SDS	

TYPICAL PERFORMANCE

LOCTITE[®] SF 7400[™] dries by the evaporation of solvent to leave a pigmented film of organic polymer. When fully dried, it has excellent visibility and shows good adhesion to a wide range of polymers and metals.

Even when fully dried, LOCTITE[®] SF 7400[™] will re-dissolve in solvents but the rate is slow. Removal of the cured film by mechanical action followed by wiping off the residues with butyl acetate or MEK is the most effective method of removal.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be used with chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use:

1. Some settling of the pigment will occur on storage. Thoroughly shake the container to re-disperse the pigment prior to use.
2. Allow the product to stand before use to eliminate air bubbles created by the pigment dispersion step.
3. Apply LOCTITE[®] SF 7400[™] to the surface.

4. Thin films of LOCTITE[®] SF 7400[™] (100 micron) will dry in approximately 5 minutes to a tack free surface at room temperature. Thicker films will dry on the surface in approximately 5 minutes but will require a longer time for thorough drying. LOCTITE[®] SF 7400[™] will be completely dry in approximately 6 hours.
5. Product can be removed by wiping with solvents (eg. MEK or butyl acetate) while it is still liquid.
6. Consult your local Henkel[®] Technical Services Center for information on automatic application equipment which is suitable for use with LOCTITE[®] SF 7400[™].

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

The product is classified as flammable and must be stored in an appropriate manner in compliance with relevant regulations. Do not store near oxidizing agents or combustible materials. Store product in the unopened container in a dry location. Storage information may also be indicated on the product container labelling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
µm / 25.4 = mil
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm ² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and

working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1